



## Agilent

# Torr Seal Low Vapor Pressure Resin Sealant Torr Seal Mixing System

## Data sheet



### Torr Seal Low Vapor Pressure Resin Sealant

Torr Seal epoxy resin quickly seals leaks on any type of vacuum system or component. Provided in convenient tubes, Torr Seal is solvent-free and can be used at pressures of  $10^{-9}$  Torr (mbar) and below, at temperatures from  $-45^{\circ}\text{C}$  to  $120^{\circ}\text{C}$  (bakeable temperature). Additionally, Torr Seal permits leak checking immediately after curing and bonds with many materials including metal, ceramic, and glass.

### Ordering Information

| Description  | Part Number | Weight lbs (kg) |
|--|-------------|-----------------|
| <b>Torr Seal base resin, 82 grams,</b><br>and Torr Seal hardener, 36 grams | 9530001     | 1.0 (0.45)      |



### Torr Seal Mixing System

The Torr Seal Mixing System includes an applicator gun, a premeasured Torr Seal cartridge, and an epoxy/resin mixer. The system uses the same low vapor pressure resin sealant as standard Torr Seal, while providing a systematic and scientific way of mixing the Torr Seal epoxy and resin. The applicator gun dispenses premeasured epoxy and resin from the cartridge through the mixer so that a uniform Torr Seal bead can be placed on any surface. As with the standard Torr Seal tubes, the mixing system can be used at pressures of  $10^{-9}$  Torr and below, and at temperatures from  $-45^{\circ}\text{C}$  to  $120^{\circ}\text{C}$  (bakeable temperature).

### Ordering Information

| Description  | Part Number | Weight lbs (kg) |
|--|-------------|-----------------|
| <b>Applicator gun with Torr Seal</b><br>cartridge (2 oz.) and three mixers | 9530002     | 2.00 (0.91)     |
| <b>Applicator gun only</b>   | 9530003     | 1.50 (0.68)     |
| <b>Torr Seal cartridge (2 oz.)</b> and three mixers                        | 9530004     | 0.75 (0.34)     |
| <b>Mixers only (six to a package)</b>                                      | 9530005     | 0.25 (0.11)     |



# Torr Seal Low Vapor Pressure Resin Sealant Torr Seal Mixing System

## Technical Specifications

|                             |   |
|-----------------------------|---|
| <b>Absorption</b>           | 0.30% (water, 24-hour immersion)  |
| <b>Acid Resistance</b>      | Withstands SF6 at 25 °C   |
| <b>Adhesion</b>             | Will not adhere to Teflon, Kel-F, nylon nor polypropylene   |
| <b>Carcinogenic</b>         | Does not contain any of the carcinogens listed in the OSHA Standards of November 29, 1975           |
| <b>Color</b>                | Off-white   |
| <b>Combustion</b>           | (Gasses emitted at normal temperatures)<br>NO <sub>x</sub> , CO <sub>2</sub> , H <sub>2</sub> O, CO |
| <b>Compressive Strength</b> | 10,000-psi ± 20% (at 25 °C)   |
| <b>Corrosive Properties</b> | Corrosive to copper when uncured; non-corrosive when cured  |
| <b>Cure Time</b>            | 24 hours at 25° C, 2 hours at 60° C   |
| <b>Dielectric Strength</b>  | 350 volts/mil   |
| <b>Dissipation Factor</b>   | 0.09 (at 25° C, 1 kHz)  |
| <b>Expansion, Linear</b>    | 30.3 x 10 <sup>-6</sup> in/in/ ° C (at 30° C to 90° C)  |
| <b>Flash Point</b>          | 175° C  |
| <b>Flexural Strength</b>    | 11,000 psi ± 20% (at 25° C)   |
| <b>Fungus Resistance</b>    | Very high   |
| <b>Harding Time</b>         | 1 to 2 hours at 25° C, 30 minutes at 60° C  |
| <b>Hardness</b>             | 75 - 80 Shore D   |

### Outgassing

See table below for typical sample at various temperatures

| Temperature, °C  | Cumulative Pumping<br>Time in hrs | Outgassing Rate<br>T-I/cm <sup>2</sup> /sec |
|------------------|-----------------------------------|---|
| 25               | 1                                 | 1.0 x 10 <sup>-5</sup>                      |
| 25               | 40                                | 7.5 x 10 <sup>-7</sup>                      |
| 116 (for 3 hrs)  | 43                                | 7.0 x 10 <sup>-5</sup>                      |
| 135 (for 9 hrs)  | 52                                | 8.0 x 10 <sup>-6</sup>                      |
| 130 (for 14 hrs) | 66                                | 2.0 x 10 <sup>-6</sup>                      |

|                         |  |
|-------------------------|--|
| <b>Heat of Reaction</b> | Very slightly exothermic   |
| <b>Pressure Range</b>   | Suitable for use in pressures of 10 <sup>-9</sup> Torr and below |
| <b>Pot Life</b>         | 55 minutes (100 grams at 25 °C)                                  |

### Radiation

Similar epoxy resins have been tested to 10<sup>11</sup> ergs of gamma radiation without noticeable effect. Torr Seal is a rigid epoxy resin (as opposed to other epoxies which have plasticizers added); all rigid epoxies are relatively impervious to damage from radiation (as compared to other organic materials such as silicone rubber, phenolics and polyesters)

|                            |  |
|----------------------------|--|
| <b>Resistivity, Volume</b> | 3.52 x 10 <sup>14</sup> ohms/cm (at 25° C) |
|----------------------------|--|

### Shear Strength, Tensile (on an aluminum lap joint)

|  |  |
|--|--|
|  | at 25 °C, following 7 days at -45 °C, 2150 psi |
|  | at 25 °C, following 7 days at 25 °C, 2000 psi  |
|  | at 25 °C, following 7 days at 80 °C, 1900 psi  |
|  | at 80 °C, 800 psi                              |
|  | 100% relative humidity, long-term, 1900 psi    |
|  | immersed in alcohol, 0.5 hour, 1600 psi        |
|  | after 24-hour room temperature cure, 800 psi   |

|                             |  |
|-----------------------------|--|
| <b>Shelf Life</b>           | 12 months minimum from date of shipment from Varian      |
| <b>Shrinkage, Linear</b>    | 0.00125 in/in (at 25° C)                                 |
| <b>Specific Gravity</b>     | 1.6  |
| <b>Solvent</b>              | Call Technical Support (800-882-7426)                    |
| <b>Temperature</b>          | -45° C to 120° C; cracks at LN <sub>2</sub> temperatures |
| <b>Tensile Strength</b>     | 5000-psi ± 30%   |
| <b>Thermal Conductivity</b> | 10.4 x 10 <sup>-4</sup> cal/sec/cm <sup>2</sup> /° C/cm  |
| <b>Toxicity</b>             | Known in cured product - none                            |
| <b>Viscosity</b>            | Thick non-flow paste                                     |

### North and South America

Agilent Technologies  
121 Hartwell Avenue, Lexington MA 02421, USA  
Tel: +1 781 861 7200, Fax: +1 781 860 5437  
Toll free: +1 800 882 7426  
vpl-customerservice@agilent.com

### Europe and other countries

Agilent Technologies Italia SpA  
via F.lli Varian 54, 10040 Leini, (Torino), Italy  
Tel: +39 011 9979 111, Fax: +39 011 9979 350  
Toll free: 00 800 234 234 00  
vpt-customerservice@agilent.com

This information is subject to change without notice.

© Agilent Technologies, Inc. 2014  
Published in Italy, Feb, 2014

